

# SUS304(A2-70)

# 参考締付トルク・軸力値一覧

サイズ	呼び径	有効断面積	強度 70	軸力 F × 0.6	締付トルク			軸力 F × 0.7	締付トルク			軸力 F × 0.8	締付トルク		
					K=0.1	K=0.15	K=0.2		K=0.1	K=0.15	K=0.2		K=0.1	K=0.15	K=0.2
	m	mm <sup>2</sup>	450N/mm <sup>2</sup>	kN	N・m			kN	N・m			kN	N・m		
M6	0.006	20.1	9.0	5.4	3.3	4.9	6.5	6.3	3.8	5.7	7.6	7.2	4.3	6.5	8.7
M8	0.008	36.6	16.5	9.9	7.9	11.9	15.8	11.5	9.2	13.8	18.4	13.2	10.5	15.8	21.1
M10	0.010	58	26.1	15.7	16	23	31	18.3	18	27	37	20.9	21	31	42
M12	0.012	84.3	37.9	22.8	27	41	55	26.6	32	48	64	30.3	36	55	73
M14	0.014	115	51.8	31.1	43	65	87	36.2	51	76	101	41.4	58	87	116
M16	0.016	157	70.7	42.4	68	102	136	49.5	79	119	158	56.5	90	136	181
M18	0.018	192	86.4	51.8	93	140	187	60.5	109	163	218	69.1	124	187	249
M20	0.020	245	110.3	66.2	132	198	265	77.2	154	232	309	88.2	176	265	353
M22	0.022	303	136.4	81.8	180	270	360	95.4	210	315	420	109.1	240	360	480
M24	0.024	353	158.9	95.3	229	343	457	111.2	267	400	534	127.1	305	457	610
M27	0.027	459	206.6	123.9	335	502	669	144.6	390	586	781	165.2	446	669	892
M30	0.030	561	252.5	151.5	454	682	909	176.7	530	795	1060	202.0	606	909	1212
M33	0.033	694	312.3	187.4	618	928	1237	218.6	721	1082	1443	249.8	824	1237	1649
M36	0.036	817	367.7	220.6	794	1191	1588	257.4	926	1390	1853	294.1	1059	1588	2118
M39	0.039	976	439.2	263.5	1028	1542	2055	307.4	1199	1799	2398	351.4	1370	2055	2741
M42	0.042	1120	504.0	302.4	1270	1905	2540	352.8	1482	2223	2964	403.2	1693	2540	3387
M45	0.045	1310	589.5	353.7	1592	2387	3183	412.7	1857	2785	3714	471.6	2122	3183	4244
M48	0.048	1470	661.5	396.9	1905	2858	3810	463.1	2223	3334	4445	529.2	2540	3810	5080
M52	0.052	1760	792.0	475.2	2471	3707	4942	554.4	2883	4324	5766	633.6	3295	4942	6589
M56	0.056	2030	913.5	548.1	3069	4604	6139	639.5	3581	5371	7162	730.8	4092	6139	8185
M64	0.064	2680	1206.0	723.6	4631	6947	9262	844.2	5403	8104	10806	964.8	6175	9262	12349